

# Water-gas shift catalysis

---

Sara Yu Choung, John Krebs, Magali Ferrandon,  
Razima Souleimanova, Deborah Myers,  
and Theodore Krause

Chemical Engineering Division  
Argonne National Laboratory



Hydrogen, Fuel Cells, and  
Infrastructure Technologies  
2003 Merit Review  
Berkeley, CA  
May 19-22, 2003

# Objective is to develop water-gas shift catalysts for on-board fuel processing

---

- Meet the DOE technical targets of
  - ✓ gas-hourly space velocity (GHSV)  $\geq 30,000 \text{ h}^{-1}$
  - ✓ CO conversion of  $\geq 90\%$
  - ✓ selectivity of  $\geq 99\%$
  - ✓ lifetime of  $> 5000 \text{ h}$
  - ✓ cost of  $< \$1/\text{kW}_e$
- Address issues with commercial CuZn catalysts
  - ✓ Eliminate the need for well-controlled *in situ* preactivation
  - ✓ Improve tolerance to temperature excursions
  - ✓ Eliminate the need to sequester during shutdown

This work addresses technical barriers J, L, and N.

# Approach

---

- Explore metal/support combinations that exhibit the bifunctional mechanism.



\* = metal surface site, adsorbs CO



oxidation of CO via oxygen  
transfer from support



reoxidation of support via  
dissociation of water

- Metals (Pt, Ru, Co, Cu) that have CO adsorption energies between 20-50 kcal/mol.
- Metal oxides that exhibit redox activity under WGS reaction conditions.

# *Industrial collaborations/interactions*

---


- Work For Others (WFO) contract with Toyota Motor Corporation to develop WGS catalysts.
- Cu/oxide and Pt/mixed oxide samples are being evaluated by
  - ✓ Nissan Motor Corporation
  - ✓ Aspen Systems
  - ✓ H2Gen Innovations

# *Reviewers' comments from FY2002 Annual Review*

---

- Activities too low to meet DOE target for GHSV.  
Increased the activity of our Pt catalyst with a bimetallic formulation.
- More emphasis on deactivation is needed.  
Investigated the effects of temperature,  $\text{H}_2\text{S}$ , and  $\text{CO}_2$  on the rate of deactivation of our Pt catalyst resulting in decreased deactivation with a bimetallic formulation.
- Select additional mixed-oxide systems for study to improve activity and durability.  
Investigated the effect of dopants to increase the activity of Ce-based catalysts. Also investigated other oxide promoters.
- More emphasis on sulfur tolerance.  
Working on it with some interesting results.

# Project timeline



# *FY2003 accomplishments*

---

- Pt catalysts
  - ✓ Improved the activity and stability of the Pt-Ce catalysts with a bimetallic formulation.
  - ✓ Identified Zr and Gd as dopants for ceria that can improve shift activity at temperatures  $>300^{\circ}\text{C}$  compared to undoped Pt-Ce.
  - ✓ Demonstrated that 5 ppm  $\text{H}_2\text{S}$  does not contribute to deactivation of Pt-Ce catalyst at  $300^{\circ}\text{C}$  but does promote deactivation at  $400^{\circ}\text{C}$ .
- Non-Pt catalysts
  - ✓ Identified Cu sintering and oxide agglomeration as modes of deactivation for Cu/mixed oxide catalyst.
  - ✓ Investigated Re, Ni-Re, and Mn as promoters to enhance the activity of Cu catalysts.

# *Use of modeling helps define our goals*

---

- The shift reaction is under kinetic control over the temperature range of 280-375°C.
- The activity of precious metal catalysts must be increased by a factor of 4 to achieve the GHSV target of 30,000 h<sup>-1</sup>.
- The merit of increasing the water content to improve the kinetics and to raise the temperature of the low temperature shift reactor is being evaluated.





## *For Pt-CeO<sub>2</sub>, our effort is directed to improve H<sub>2</sub>O dissociation and oxygen transfer rates*

---

- Kinetic studies\* show that the rate is zeroth order in CO and half-order in H<sub>2</sub>O (rate  $\propto P_{\text{CO}}^0 P_{\text{H}_2\text{O}}^{0.5}$ )
  - ✓ Metal surface is saturated with CO
  - ✓ Reaction may be controlled by
    - rate of reoxidation of ceria by water
    - rate of oxygen transfer from ceria to metal interface
    - metal dispersion and surface area
- Improve ceria redox/oxygen transfer rates by cation doping
- Improve water dissociation on Pt surface by addition of a second metal
- Stabilize Pt against sintering

\* Bunluesin et al., *Appl. Catal. B* **15** (1998) 107-114; Hilaire et al., *Appl. Catal. A* **215** (2001), 271-278; Wang et al., *J. Catal.* **212** (2002) 213-230.


## CO conversion per mole of Pt was independent of Pt loading from 0.87-2.86 wt%



Conditions: 6.9% CO, 10.35% CO<sub>2</sub>, 20.7% N<sub>2</sub>, 31.05% H<sub>2</sub>, 31.0% H<sub>2</sub>O  
GHSV = 600,000-1,800,000 h<sup>-1</sup>, 0.05-0.1 ml catalyst diluted with  $\alpha\text{-Al}_2\text{O}_3$

- By increasing the Pt loading, the CO conversion per unit volume of reactor can be increased.
- Increasing the Pt loading will make it difficult to achieve the cost target of  $\$1/\text{kW}_e$ .


## *Doping CeO<sub>2</sub> with Gd or Zr increased activity at temperatures above 300°C*



Conditions: 6.9% CO, 10.35% CO<sub>2</sub>, 20.7% N<sub>2</sub>, 31.05% H<sub>2</sub>, 31.0% H<sub>2</sub>O  
GHSV = 600,000 h<sup>-1</sup>, 0.1 ml catalyst diluted with 0.4 ml α-Al<sub>2</sub>O<sub>3</sub>

- Doping CeO<sub>2</sub> is known to lower the temperature at which Ce<sup>4+</sup> reduction occurs and to increase oxygen release rates.
- Our results suggest that doping Ce will not significantly improve its activity below 300°C.



## Increased the activity by a factor ~2 with certain Pt bimetallic formulations



Conditions: 6.9% CO, 10.35% CO<sub>2</sub>, 20.7% N<sub>2</sub>, 31.05% H<sub>2</sub>, 31.0% H<sub>2</sub>O  
GHSV = 200,000-1,500,000 h<sup>-1</sup>, 0.05-0.4 ml catalyst diluted with  $\alpha\text{-Al}_2\text{O}_3$



- Selection of bimetallic formulation based on theoretical studies of the energetics of H<sub>2</sub>O dissociation and reaction between CO<sub>ads</sub> + OH<sub>ads</sub> on Pt-mixed metal clusters (Ishikawa et al., *Surface Science* **513** (2002) 98-110).

*~50% loss of activity was observed over 40 h at both 300 and 400°C with Pt catalyst*




Conditions: 6.9% CO, 10.35% CO<sub>2</sub>, 20.7% N<sub>2</sub>, 31.05% H<sub>2</sub>, 31.0% H<sub>2</sub>O  
GHSV = 300,000-1,200,000 h<sup>-1</sup>, 0.03-0.1 ml catalyst diluted with  $\alpha\text{-Al}_2\text{O}_3$

# *5 ppm $H_2S$ increased the rate of deactivation at 400°C, but not at 300°C with Pt catalyst*






Conditions: 5 ppm  $H_2S$ , 6.9% CO, 10.35%  $CO_2$ , 20.7%  $N_2$ , 31.05%  $H_2$ , 31.0%  $H_2O$   
GHSV = 300,000-1,200,000  $h^{-1}$ , 0.03-0.1 ml catalyst diluted with  $\alpha-Al_2O_3$

## *Pt+A bimetallic was more stable than Pt at 300°C*




Conditions: 6.9% CO, 10.35% CO<sub>2</sub>, 20.7% N<sub>2</sub>, 31.05% H<sub>2</sub>, 31.0% H<sub>2</sub>O  
GHSV = 300,000-400,000 h<sup>-1</sup>, 0.10-0.12 ml catalyst diluted with  $\alpha\text{-Al}_2\text{O}_3$

# Deactivation of Cu/mixed oxide at $>300^{\circ}\text{C}$ likely caused by sintering of Cu and agglomeration of oxide






# Investigated Ni and Re as promoters for improving activity and stability of Cu catalysts operating at 250-400°C




- Our previous work has shown that Re stabilizes Co-based catalysts.
- Ni and Cu form a solid solution that can accommodate  $\sim 10$  atom% Re.

# *Investigated Mn as a promoter for improving activity and stability of Cu catalysts operating at 250-400°C*

Rate observed with fresh sample



Rate after air exposure



Conditions: 6.9% CO, 10.35% CO<sub>2</sub>, 20.7% N<sub>2</sub>, 31.05% H<sub>2</sub>, 31.0% H<sub>2</sub>O, GHSV = ~40,000 h<sup>-1</sup>

- Mn enhances Cu activity as observed with Re and Ni-Re.
- Cu-Mn is more active than Cu after air exposure at >350°C.

# FY2003 milestones

---

<u>Milestone</u>	<u>Date</u>
Improve low-temperature (<250°C) activity of catalyst to >9 $\mu\text{moles CO g}^{-1} \text{ s}^{-1}$ . <i>We have developed a Cu that yields 10 <math>\mu\text{moles CO g}^{-1} \text{ s}^{-1}</math> at 250°C. Long-term stability is still an issue.</i>	02/03
Complete 1000 h test of catalyst using sulfur-free synthetic reformat.	02/03
<i>We have completed a 250 h test of Pt-Ce that we have extrapolated to 1000 h.</i>	
Improve sulfur tolerance of non-precious metal catalyst in reformat containing 3 ppm $\text{H}_2\text{S}$ . <i>Work in progress – has proven to be challenging.</i>	06/03
Demonstrate $\leq 1\%$ CO out using a structured form of the catalyst(s). <i>Coating of monoliths is in progress. Testing to begin 6/03.</i>	09/03

# Future work

---

- Pt-Ce catalysts
  - ✓ Optimize bimetallic formulation to increase activity while decreasing Pt loading to achieve DOE cost target
  - ✓ Retard Pt sintering
  - ✓ Address H<sub>2</sub>S poisoning at temperature of 400°C
  - ✓ Evaluate catalyst performance on monolith
- Cu catalysts
  - ✓ Increase low temperature (230-300°C) activity
  - ✓ Reduce Cu sintering through the addition of promoters to improve stability
  - ✓ Improve sulfur tolerance
- Conduct characterization studies (SEM/TEM and EXAFS/XANES) to improve activity and reduce deactivation.